

Underlay Technical Specification

Item Code: TABOARDWALK2


Issue Date: 13/3/2013

Issue No. 8

Sponge Rubber

Suitable for floating installation of laminate and solid timber floors

Suitable for use with underfloor heating



Standard Specifications

Nominal square weight †	2545 g/m ² (75 oz/yd ²)
Roll area*	15.07m ² (1.37m x 11.0m)

BS 5808: 1991

Nominal thickness†	3.60mm	BS 4051
Work of compression Minimum 50 J/m ²	57 J/m ²	BS 4908 & BS 4052
Retention of work of compression (min 40%)	79 %	BS 4908 & BS 4052
Compression after dynamic loading	2.2 mm	BS 4908 & BS 4052
Loss in thickness after dynamic loading (max 15%)	4.7 %	BS 4052
Loss in thickness after static loading (max 15%)	7.7 %	BS 3939
Resistance to cracking (not greater than 50mm)	Pass	BS 5808

Flammability

Hot metal nut test (tested in Interfloor laboratory)	Medium radius of effects of ignition	BS 4790 & BS 5287
--	--------------------------------------	-------------------

Acoustic Sone wood/laminate flooring test

Drum sound emission (overall loudness) (Sone)	56	EPLF-Norm 021029-1
Impact sound reduction (Delta Lw)	23dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997

Other Specifications

Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
Colour / backing	Black / gold Varpourstop membrane	
Packaging	Yellow film / green print	
Thermal resistance	0.55 togs	BS 4745
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

Certification



Guarantee

Guaranteed for the serviceable lifetime of the flooring.

Notes

* The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

† ±5%

‡ Value derived from similar product test results