

## Underlay Technical Specification

Item Code: TADREAMWALK3


Issue Date: 19/8/2014

Issue No. 1

### Polyurethane Rebond

**Suitable for stretch-fit installation of carpets**

**End Use Classification (BS 5808: 1991): L/U, Luxury Use**



#### Standard Specifications

Nominal density <sup>†</sup>	110 kg/m <sup>3</sup>
Nominal square weight <sup>†</sup>	1287 g/m <sup>2</sup>
Nominal roll weight <sup>†</sup>	19.30 kg
Roll area*	15.07m <sup>2</sup> (1.37m x 11.0m)

#### BS 5808: 1991

End Use Classification	L/U, Luxury Use	
Nominal thickness	11.00mm	BS 4051
Work of compression Minimum 50 J/m <sup>2</sup>	>160 J/m <sup>2</sup>	BS 4098 & BS 4052
Retention of work of compression (min 40%)	>80 %	BS 4098 & BS 4052
Loss in thickness after dynamic loading (max 15%)	<5 %	BS 4052
Loss in thickness after static loading (max 15%)	<5 %	BS 4939
Resistance to cracking (not greater than 50mm)	Pass	BS 5808

#### Flammability

Hot metal nut test (tested in Interfloor laboratory)	Low radius of effects of ignition	BS 4790 & BS 5287
--	-----------------------------------	-------------------

#### Other Specifications

Odour	No objectionable odour	
Colour / backing	Blue / white printed Textron® backing	
Packaging	White film / red print	
Thermal resistance	3.13 togs	BS 4745
Impact sound reduction (Delta Lw)	44 dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

#### Certification



#### Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

#### Notes

\* The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

† ±5%

‡ Value derived from similar product test results