

Underlay Technical Specification

Item Code: TADK080013

Issue Date: 05/01/2021

Issue No. 8

Sponge Rubber

Suitable for the stretch-fit installation of carpets

Suitable for underfloor heating. We do not recommend an underlay is used with an electric mat (or dry) underfloor heating system

End Use Classification (BS 5808: 1991 / BS EN 14499 : 2015): L/U, Luxury Use



Standard Specifications*

Nominal square weight	4238 g/m ² (125 oz/yd ²)	
Nominal roll weight	46.6 kg (102 lb)	
Nominal roll area	10.96m ² (1.33m x 8.24m)	
Nominal thickness	8.30mm	ISO 1765

BS 5808: 1991 / EN14499 : 2015

End Use Classification	L/U, Luxury Use	
Work of compression (Min. 50 J/m ² Max. 200 J/m ²)	150 J/m ²	BS 4098 & ISO 2094
Retention of work of compression (min 40%)	98 %	BS 4098 & ISO 2094
Compression after dynamic loading	4.6 mm	BS 4098 & ISO 2094
Loss in thickness after dynamic loading (max 15%)	2.5%	BS 4052 & ISO 2094
Loss in thickness after static loading (max 15%)	3.0 %	ISO 3415/3416 & BS 4939
Breaking strength (length/width) min. 30N	182N / 126N	EN ISO 13394 BS 2576
Extension under force (length/width) max. 15% @ 30N	2.2 % / 1.0 %	EN ISO 13394 BS 2576
Resistance to cracking (not greater than 50mm)	Pass	EN 14499 & BS 5808


Flammability

Hot metal nut test (tested in Interfloor laboratory)	Low radius of effects of ignition	BS 4790 & BS 5287
Russian GOST FR Test	Classification KM5	

Other Specifications

Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
Colour / backing	Black / printed Textron® backing	
Packaging	Cream film / blue print	
Thermal resistance	0.80 togs	BS 4745
Impact sound reduction (Delta Lw)	42 dB ‡	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

Certification



Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

Notes

* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015

‡ Value derived from similar product test results