SILENTFLOOR



Underlay Technical Specification

Item Code: TASIL

Issue No. 11

Issue Date: 05/01/2021

Sponge Rubber

Suitable for use under contract carpets and for the floating installation of laminate and solid timber floors Suitable for underfloor heating. We do not recommend an underlay is used with an electric mat (or dry) underfloor heating system

Standard Specifications*		
Nominal square weight	2204 g/m ² (65 oz/yd ²)	
Nominal roll weight	32.21 kg	
Nominal roll area	15.07m ² (1.37m x 11.0m)	
Nominal thickness	3.00 mm	ISO 176
BS 5808: 1991 / EN14499 : 2015		
Mean original thickness from nominal thickness (Max.12%)	1.6 %	ISO 176
Difference between max. & min. original thicknesses (Max.3mm)	0.3 mm	ISO 176
Tensile strength (length/width)	870 kPa / 300 kPa EN ISO	1798:200
Elongation @ break (length/width)	80 % / 140 % EN ISO	1798:200
Compressive stress @ 25 % strain	95 kPa EN ISO 3386	8 Pt 2: 199
Compressive stress @ 50 % strain	750 kPa EN ISO 3386	8 Pt 2: 199
Electrical Resistivity		
Vertical resistance, 25% RH Vertical resistance, 65% RH Horizontal resistance, 25% RH Horizontal resistance, 65% RH Vertical resistivity, 25% RH Vertical resistivity, 65% RH Horizontal resistivity, 25% RH Horizontal resistivity, 65% RH	1.3 x 10 ¹ 2 ohms 1.2 x 10 ¹ 2 ohms 8.3 x 10 ¹ 2 ohms 2.5 x 10 ¹ 2 ohms 58 x 10 ¹ 2 ohms/cm ² 58 x 10 ¹ 2 ohms/cm ² 76 x 10 ¹ 2 ohms/cm ² 28 x 10 ¹ 2 ohms/cm ²	BS 663 BS 663 BS 663 BS 663 BS 663 BS 663 BS 663
Flammability		
Reaction to fire classification	Cfl - s1 ISO9239-1 & 11925-2, rated to	EN13501
Acoustic Sone wood/laminate flooring test		
Drum sound emission (overall loudness) (Sone)	55 EPLF-Norr	n 021029
Impact sound reduction (Delta Lw)	20 dB BSEN ISO 140-8: 1998 and BSEN ISO	717-2: 199
Other Specifications		
Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
Colour / backing	Gold / unprinted Textron [®] backing	
Packaging	Clear, with printed insert	
Thermal resistance	0.38 togs	BS 474
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

Guarantee

Certification

Guaranteed for the serviceable lifetime of the flooring.

urala

Low emission interior materials

Notes

* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015

[‡] Value derived from similar product test results

interfloor

Interfloor Ltd., Broadway, Haslingden, Rossendale, Lancashire, BB4 4LS. Tel: +44(0)1706 213131 Fax: +44(0)1706 214737 Web: www.interfloor.com International Enquiries: Telephone: +44(0)1706 238825 Fax: +44(0)1706 225114