

TIMBERMATE EXCEL

Underlay Technical Specification

Item Code: TATEX11013

Issue Date: 22/07/2021

Issue No. 7

Sponge Rubber

Suitable for the floating installation of laminate and solid timber floors

Suitable for underfloor heating. We do not recommend an underlay is used with an electric mat (or dry)

underfloor heating system



Nominal square weight	2545 g/m² (75 oz/yd²)
Nominal density	707 kg/m³
Nominal roll weight	38.3 kg
Nominal roll area	15.07m ² (1.37m x 11.00m)
Nominal thickness	3.60 mm (0.14") ISO 1765



BS 5808: 1991 / EN14499 : 2015

Mean original thickness from nominal thickness (Max.12%)	1.2 %	ISO 1765
Difference between max. & min. original thicknesses (Max.3mm)	0.3 mm	ISO 1765
Work of compression (Min. 50 J/m² Max. 200 J/m²)	57 J/m²	BS 4098 & ISO 2094
Retention of work of compression (min 40%)	79 %	BS 4098 & ISO 2094
Compression after dynamic loading	2.2 mm	BS 4098 & ISO 2094
Breaking strength (length/width) min. 30N	242N / 106N	EN ISO 13394 BS 2576
Extension under force (length/width) max. 15%@ 30N	0.5% / 0.6%	EN ISO 13394 BS 2576
Loss in thickness after dynamic loading (max 15%)	4.7 %	BS 4052 & ISO 2094
Loss in thickness after static loading (max 15%)	7.7 %	ISO 3415/3416 & BS 4939



Flammability

Hot metal nut test (Not greater than 50mm)	Low radius of effects of ignition	BS 4790 & BS 5287
Anti Flammability	Grade Level 1	CNS7614
Reaction to fire classification	Cfl-s1 &11:	Tested to ENISO9239-1 925-2, rated to EN13501-1
Russian GOST FR Test	Classification KM5	



Electrical Resistivity

Vertical resistance, 25% RH
Horizontal resistance, 25% RF
Vertical resistivity, 25% RH
Horizontal resistivity, 25% RH

>10.0 x 10 12 ohms >5.0 x 10 14 ohms/cm² >9.0 x 10 13 ohms/cm² >10.0 x 10 12 ohms BS 6654 Vertical resistance, 65% RH Horizontal resistance, 65% RH Vertical resistivity, 65% RH

Horizontal resistivity, 65% RH

>10.4 x 10 8 ohms >2.7 x 10 8 ohms >5.2 x 10 10 ohms/cm² >2.4 x 10 9 ohms/cm² BS 6654

Certification



Guarantee

Guaranteed for the serviceable lifetime of the flooring.

Notes

* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015

THIS PRODUCT IS PRODUCED IN A FACILITY ACCREDITED TO ISO 9001, 14001 & 45001






TIMBERMATE EXCEL

Underlay Technical Specification

Item Code: TATEX11013

Issue Date: 22/07/2021

Issue No. 7







Other Specifications		
Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
Colour / backing	Green / silver printed Vapourstop membrane	
Packaging	Clear, with printed insert	
Thermal resistance	0.55 togs BS 4745	
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria Certified GLP051 Cat CC10 Rubber US CRI Green Label Plus Programme	



GREEN CREDENTIALS

Barrier Properties

Green Features	Description	LEED Programme
Recyclable	At the end of the underlays useful life it can be 100% recycled	MR 2.0: Points Available It can be recycled
Recycled Content	Contains not less than 3% pre-consumer recycled material	MR 4.0: Points Available Recycled Content
Indoor Air Quality	Meets or exceeds the industry standard for indoor air quality as established by the CRI Green Label Programme	IEQ 4.3: Points Available Product is Green
		Label Certified
Regional Materials	Production Facility Haslingden BB4 4LS, UK Where used within 500 miles of Production Facility	MR 5.0: Points Available



LEED points must be considered along with other building components and must be determined by the specifier/architect or LEED accredited professional

Certification





Guarantee

Guaranteed for the serviceable lifetime of the flooring.

Notes

* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015

THIS PRODUCT IS PRODUCED IN A FACILITY ACCREDITED TO ISO 9001, 14001 & 45001

