

Underlay Technical Specification

Item Code: TAWILLOW

Issue Date: 4/3/2014

Issue No. 9

Sponge Rubber

Suitable for the stretch-fit installation of carpets

End Use Classification (BS 5808: 1991): GD/U, General Domestic Use



Standard Specifications

Nominal square weight†	2712 g/m ² (80 oz/yd ²)
Nominal roll weight†	40.86 kg
Roll area*	15.07m ² (1.37m x 11.00m)

BS 5808: 1991

End Use Classification	GD/U, General Domestic Use	
Nominal thickness†	8.40mm	BS 4051
Mean original thickness from nominal thickness (max. 12%)	4.0 %	BS 4051
Difference between max. & min. original thickness (max. 3mm)	0.5 mm	BS 4051
Work of compression Minimum 50 J/m ²	108 J/m ²	BS 4908 & BS 4052
Retention of work of compression (min 40%)	70 %	BS 4908 & BS 4052
Compression after dynamic loading	5.3 mm	BS 4908 & BS 4052
Loss in thickness after dynamic loading (max 15%)	6.3 %	BS 4052
Loss in thickness after static loading (max 15%)	7.3 %	BS 4939
Breaking strength (length/width) min. 40N	182N / 126N	BS 2576
Extension under force (length/width) max. 10%@ 40N	2.2% / 1.0%	
Resistance to cracking (not greater than 50mm)	Pass	BS 5808

Flammability

Hot metal nut test	Low radius of effects of ignition	BS 4790 & BS 5287
Russian GOST FR Test	Classification KM5	GOST 30244-94, GOST 30402-96 GOST 51032-97, GOST 12.1.044-89 (item 4.18), GOST 12.1.044-89 (item 4.20)

Certification



Other Specifications

Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
Colour / backing	Forest green / unprinted Textron® backing	
Packaging	Green film / green print	
Thermal resistance	1.1 togs	BS 4745
Impact sound reduction (Delta Lw)	32 dB ‡	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

Notes

* The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

† ±5%

‡ Value derived from similar product test results