

Underlay Technical Specification

Item Code: TATITANIUM4

Issue Date: 20/05/2022

Issue No.1



Polyurethane Rebond

Suitable for stretch fit and double stick* installations of carpets (*for areas up to 30m²)

End Use Classification (BS 5808: 1991 / BS EN 14499 : 2015): HCU, Heavy Contract Use

Standard Specifications*

Nominal density	180 kg/m ³	
Nominal square weight	1495 g/m ²	
Nominal roll weight	22.5 kg	
Nominal roll area	15.07m ² (1.37m x 11.0m)	
Nominal thickness	8.00mm	ISO 1765

BS 5808: 1991 / EN14499 : 2015

End Use Classification	HC/U, Heavy Contract Use	
Work of compression (Min. 50 J/m ² Max. 200 J/m ²)	>140 J/m ²	BS 4098 & ISO 2094
Retention of work of compression (min 40%)	>90 %	BS 4098 & ISO 2094
Loss in thickness after Dynamic loading (max 15%)	<5 %	BS 4052 & ISO 2094
Loss in thickness after static loading (max 15%)	<4 %	ISO 3415/3416 & BS 4939
Breaking strength (length/width) min. 30N	>90N / >50N	EN ISO 13394 BS 2576
Extension under force (length/width) max. 15% @ 30N	<10% / <10%	
Resistance to cracking (not greater than 50mm)	Pass	EN 14499 & BS 5808

Flammability

Hot metal nut test (tested in Interfloor laboratory)	Low radius of effects of ignition	BS 4790 & BS 5287
--	-----------------------------------	-------------------

Other Specifications

Odour	No objectionable odour	
Colour / backing	Grey film with black print / grey film and mesh	
Packaging	White film / violet & purple print	
Thermal resistance	2.22 togs	BS 4745
Impact sound reduction (Delta Lw)	39dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

Certification



Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

Notes

- * The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015
- ‡ Value derived from similar product test results

THIS PRODUCT IS PRODUCED IN A FACILITY ACCREDITED TO ISO 9001, 14001 & 45001